

Primary lithium-thionyl chloride(Li-SOCl₂)

ER14505M

Electrical Characteristics

Typical values relative to cells stored for one year or less at + 25°C max.

Nominal Capacity

At 2mA, +23°C, 2.0V cut-off. The capacity restored by the cell varies according to current drain, temperature and cut-off. The cut-off voltage below 2.0V, consult GREEN ENERGY.

2200mAh

Max. Recommended Continuous Current

At 400mA, $+23^{\circ}$ C, 2.0V cut-off. The capacity was 50% of nominal capacity.

400mA

Max. Pulse Current

800mA/0.1second pulses, drained every 2 min at +23°C from undischarged cells with 10uA base current, yield voltage readings above 3.0V. The readings may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult GREEN ENERGY.

800mA

Storage (Recommended) $+20^{\circ}\text{C} \sim +25^{\circ}\text{C}$

Operating Temperature Range

Operation above ambient temperature may lead to reduced capacity and lower voltage readings at the beginning of pulses.

-55°C ~ +85°C

Diameter	Max. 14.5mm

Height Max. 51mm

Typical Weight Approx. 19g

Li Metal Content Approx. 0.6g



AA-size spiral cell

Key Features

- High and stable operating voltage
- Low self-discharge rate (less than 2% after 1 year of storage at +20°C)
- Wide operating temperature range (-55°C ~ +85°C)/(-67°F ~ +185°F)
- Stainless steel container and cap
- Hermetic glass-to-metal sealing
- Non-restricted for transport


Main Applications

- Radiocommunication and other military applications
- Alarms and security systems
- Beacons and emergency location transmitters
- GPS
- Metering systems
- Tracking systems
- GSM communication

Note: Information above just for your reference, more details please contact Green Energy Battery Co., Ltd.



Performance



Note:Information above just for your reference, more details please contact Green Energy Battery Co.,Ltd.