

Primary lithium-thionyl chloride(Li-SOCl₂)

ER18505

[Electrical Characteristics]

Typical values relative to cells stored for one year or less at + 25°C max.

Nominal	Voltage	
---------	---------	--

3.6V

Nominal Capacity

At 1mA, +23°C, 2.0V cut-off. The capacity restored by the cell varies according to current drain, temperature and cut-off. The cut-off voltage below 2.0V, consult GREEN ENERGY.

4100mAh

Max. Recommended Continuous Current

At 100mA, +23°C, 2.0V cut-off. The capacity was 50% of nominal capacity.

100mA

Max. Pulse Current

200mA/0.1second pulses, drained every 2 min at +23°C from undischarged cells with 10uA base current, yield voltage readings above 3.0V. The readings may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult GREEN ENERGY.

200mA

Storage (Recommended)

+20°C ~ +25°C

Operating Temperature Range

Operation above ambient temperature may lead to reduced capacity and lower voltage readings at the beginning of pulses.

-55°C ~ +85°C

Diameter

Max. 18.5mm

Height

Max. 51mm

Typical Weight

Approx. 32g

Li Metal Content

Approx. 1.05g



Key Features

- High and stable operating voltage
- Low self-discharge rate (less than 2% after 1 year of storage at +20°C)
- Wide operating temperature range (-55°C ~ +85°C)/(-67°F ~ +185°F)
- Stainless steel container and cap
- Hermetic glass-to-metal sealing
- RoHS compliant


Main Applications

- Utility metering
- Alarms and security devices
- Memory back-up
- Tracking systems
- Automotive electronics
- Professional electronics

Note: Information above just for your reference, more details please contact Green Energy Battery Co., Ltd.



Performance



Note:Information above just for your reference, more details please contact Green Energy Battery Co.,Ltd.