

Primary lithium-thionyl chloride(Li-SOCl₂)

ER26500

Electrical Characteristics

Typical values relative to cells stored for one year or less at + 25°C max.

Nominal Voltage

Nominal Capacity

At 2mA, +23°C, 2.0V cut-off. The capacity restored by the cell varies according to current drain, temperature and cut-off. The cut-off voltage below 2.0V, consult GREEN ENERGY.

8600mAh

3.6V

Max. Recommended Continuous Current

At 200mA, $+23^{\circ}$ C, 2.0V cut-off. The capacity was 50% of nominal capacity.

200mA

Max. Pulse Current

400mA/0.1second pulses, drained every 2 min at +23°C from undischarged cells with 10uA base current, yield voltage readings above 3.0V. The readings may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult GREEN ENERGY.

400mA

Storage (Recommended) $+20^{\circ}\text{C} \sim +25^{\circ}\text{C}$

Operating Temperature Range

Operation above ambient temperature may lead to reduced capacity and lower voltage readings at the beginning of pulses.

-55°C ~ +85°C

Diameter Max. 26.2mm

Height Max. 50mm

Typical Weight Approx. 55g

Li Metal Content Approx. 2.3g



Key Features

- High and stable operating voltage
- Low self-discharge rate (less than 2% after 1 year of storage at +20°C)
- Wide operating temperature range $(-55^{\circ}\text{C} \sim +85^{\circ}\text{C})/(-67^{\circ}\text{F} \sim +185^{\circ}\text{F})$
- Stainless steel container and cap
- Hermetic glass-to-metal sealing
- RoHS compliant


Main Applications

- Utility metering
- Automatic meter readers
- Buoys
- Measuring equipment
- Industrial applications
- Professional electronics

Note: Information above just for your reference, more details please contact Green Energy Battery Co., Ltd.



Performance



Note:Information above just for your reference, more details please contact Green Energy Battery Co.,Ltd.