


## Primary lithium-thionyl chloride(Li-SOCl<sub>2</sub>) ER341270

Electrical Characteristics

Typical values relative to cells stored for one year or less at +  $25^{\circ}$ C max.

3.6V	Nominal Voltage
	Nominal Capacity
38000mAh	At 0.5mA, +23°C, 2.0V cut-off. The capacity restored by the cell varies according to current drain, temperature and cut-off. The cut-off voltage below 2.0V, consult GREEN ENERGY.
450mA	<b>Max. Recommended Continuous Current</b> At 50mA, +23°C, 2.0V cut-off. The capacity was 50% of nominal capacity.
	Max. Pulse Current
1000mA	100mA/0.1second pulses, drained every 2 min at +23°C from undischarged cells with 10uA base current, yield voltage readings above 3.0V. The readings may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult GREEN ENERGY.
+20°C ~ +25°C	Storage ( Recommended )
	Operating Temperature Range
-55°C ~ +85°C	Operation above ambient temperature may lead to reduced capacity and lower voltage readings at the beginning of pulses.
Max. 34.2mm	Diameter
Max. 127mm	Height
Approx. 188g	Typical Weight
Approx. 10g	Li Metal Content



Note: Information above just for your reference, more details please contact Green Energy Battery Co., Ltd.





10m/

100mA

-30

-10

10


30

3.1

2.8

-50

Discharge performance (25°C) 3.5 3.0 Voltage/V 2.5 2.0 10Ω 33Ω 350mA 100mA 330Ω 10mA 1100Ω 3.6KΩ 3mA 1mA <u>34.5Ah 31.7</u>Ah 15Ah 20Ah 38Ah 1.5 1.0 ⊾ 0.1 10  $10^{3}$  $10^{4}$ 10 10<sup>5</sup> 1 Hours **Capacity vs Current** 40 36 -30 °٢ 32 0 25 28 50 24 Capacity/Ah 72 20 16 12 8 4 0 1 10 100 1000 0.1 Current (mA) Voltage vs Temperature 3.9 3.7 0.13mA 3.5 Voltage/V 1mA 3.3



Note: Information above just for your reference, more details please contact Green Energy Battery Co., Ltd.

90

70

Temperatura/°C

50